



# Technical Data Sheet:CR91908

**Product manual** **CR91908** is a hexagon polyurethane acrylate oligomer; It has the characteristics of low viscosity, high hardness and good abrasion resistance, It mainly used in UV coatings and inks.

**Product features** Low viscosity  
High hardness and good toughness  
Good abrasion resistance

**Suggested application** Wood coatings  
Metal coatings  
Plastic coatings  
Inks

<b>Specifications</b>	Functional basis (theoretical)	6
	Appearance(By vision)	Colorless to light yellow transparent liquid
	Viscosity (CPS/60℃)	4000-8000
	Color (APHA)	≤ 100
	Efficient content(%)	100

**Packing** Net weight 50KG plastic bucket and net weight 200KG iron drum.

**Storage conditions** Resin please keep cool or dry place, and avoid sun and heat;  
Storage temperature does not exceed 40 ℃, storage conditions under normal conditions for at least 6 months.

**Use matters** Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate;  
for details, please refer to the Material Safety Instructions (MSDS);  
Each batch of goods to be tested before they can be put into production.