



Technical Data Sheet: MP5130

Product manual MP5130 is a polyurethane-modified acrylate oligomer; it has the characteristics of easy

matting, good matte powder alignment, good wettability, good adhesion to various

substrates, and good toughness. It is mainly used in wood coatings, electroplating

coatings, screen inks, etc.

Product features Fast curing speed

Good adhesion to various substrates

Good arrangement of matte powder

Recommended use Plastic coatings

Vacuum plating coatings

Wood Coatings

Inks

3 **Specifications** Functionality (theoretical)

> Appearance(By vision) Clear liquid

> Viscosity (CPS/60°C) 4000-9000

Color(Gardner) ≤1

Efficient content(%) 100

Net weight 50KG plastic bucket and net weight 200KG iron drum. **Packing**

Please keep cool or dry place, and avoid sun and heat; Storage conditions

Storage temperature does not exceed 40 °C, storage conditions under normal conditions

for at least 6 months.

Use matters Avoid touching the skin and clothing, wear protective gloves when handling;

> Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS);

Each batch of goods to be tested before they can be put into production.