



# Technical Data Sheet: ME5401

<b>Product manual</b>	<b>ME5401</b> is a modified epoxy acrylate oligomer. it has the characteristics of low viscosity, good sanding, good leveling , fast curing speed and good surface drying. It is used in wood coatings, OPV, screen inks, etc.	
<b>Product features</b>	Excellent leveling Good yellow resistance Easy to sand	
<b>Recommended use</b>	Wood coatings Plastic coatings OPV Inks	
<b>Specifications</b>	Functionality (theoretical)	2
	Appearance(By vision)	Clear liquid
	Viscosity (CPS/60℃)	3500-6800
	Color(Gardner)	≤2
	Efficient content(%)	100
	Acid value(mgKOH/g)	3.0-4.0
<b>Packing</b>	Net weight 50KG plastic bucket and net weight 200KG iron drum.	
<b>Storage conditions</b>	Please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 ℃, storage conditions under normal conditions for at least 6 months.	
<b>Use matters</b>	Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production.	