



Technical Data Sheet: **CR90671**

| | | |
|------------------------------|---|--------------|
| Product manual | CR90671 is an aliphatic urethane acrylate oligomer, that was designed for metals coatings, optical coatings, film coating and screen inks. It is a highly flexible oligomer, which offer good weatherability. | |
| Product features | Highly toughness Low viscosity Non-yellowing | |
| Suggested application | Highly weatherility coatings Encapsulants electronics, Inks Inject ink | |
| Specifications | Functional basis (theoretical) | 2 |
| | Appearance(By vision) | Clear liquid |
| | Viscosity (CPS/25℃) | 3800-8200 |
| | Color (Gardner) | ≤1 |
| | Efficient content(%) | ≥99.9 |
| Packing | Net weight 50KG plastic bucket and net weight 200KG iron drum. | |
| Storage conditions | Resin please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 °C, storage conditions under normal conditions for at least 6 months. | |
| Use matters | Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production. | |