



# Technical Data Sheet: HP6613

**Product manual** HP6613 is an aliphatic urethane hexaacrylate resin. It has the characteristics of fast curing speed, high surface hardness, good toughness and abrasion resistance; It is mainly used in UV wood, UV paint and other fields.

**Product features**

- Fast curing speed
- High surface hardness
- Good toughness
- Good abrasion resistance
- High cost-effective

**Recommended use**

- UV coating
- UV wood

<b>Specifications</b>	Functionality (theoretical)	6
	Appearance(By vision)	Colorless
	Viscosity (CPS/25℃)	30000-50000
	Color(APHA)	<60
	Efficient content(%)	100

**Packing** Net weight 50KG plastic bucket and net weight 200KG iron drum.

**Storage conditions** Please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 °C, storage conditions under normal conditions for at least 6 months.

**Use matters** Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production.