



Technical Data Sheet: HT7613

Product manual	HT7613 is a polyester acrylate oligomer; It has fast curing speed, good abrasion resistance, good adhesion, good levelling and high hardness. It is suitable for all kinds of coatings, such as plastic coatings, wood coatings, inks.	
Product features	Low viscosity Fast curing speed Good leveling Good abrasion resistance	
Recommended use	UV plastic coating UV wood coating OPV UV ink	
Specifications	Functionality (theoretical)	6
	Appearance (By vision)	Clear & Clean liquid
	Viscosity (CPS/25°C)	1400-3200
	Color (APHA)	≤ 150
	Efficient content (%)	100
Packing	Net weight 50KG plastic bucket and net weight 200KG iron drum.	
Storage conditions	Please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 °C, storage conditions under normal conditions for at least 6 months.	
Use matters	Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production.	